AMENDMENTS TO THE SPECIFICATION

Please amend the Specification as follows:

JDK 3/28

Page ~~22~~ 20, Table 2:

		Resin No.			
		1	2	3	4
Nature Works grade	4031 (mass %)	100	0	0	0
	4050 (mass %)	0	100	70	0
	4060 (mass %)	0	0	30	100
Average D-lactic acid content (mass %)		1.2	5	7.1	12

JDK 3/28

P. ~~38~~ 36, Table 3:

			Examples of the invention						
			1	2	3	4	5	6	7
Biodegradable laminated sheet	Entire sheet	Sheet thickness (μm)	300						
		Layer structure	Three layers						
		Layer arrangement *1)	1/2/1						
		Ratio of thickness	1/5/1		1/100/1	1/5/1			
		Db-Da (mass %)	10.8						
	First layers	Da (mass %)	1.2						
		Thickness (Total) (μm)	86		6	86			
		Crystallinity *2) (%)	44	45	44	47	46	40	39
		Polyester Type	PBS			PBTA	PBSL	PBSLA	PBSA

Second layers	resin	Content (mass %)	50	75	25	50					
	Db %		12								
	Thickness (Total) (μm)		214		294	214					
	Crystallinity* 2) (%)		1	1.2	1	1.3	2	1	1.3		
	Polyester resin	Type	PBS			PBTA	PBSL	PBSLA	PBSA		
		Content (mass %)	50	75	25	50					
Evaluation	Heat resistance 1 (%)		0.9	0.7	2.2	1.3	0.8	1.5	1.4		
	Heat resistance 2		o	o	o	o	o	o	o		
	Impact resistance 1 (Kgf·mm)		215	416	125	325	200	285	312		
	Impact resistance 2		o	o	o	o	o	o	o		
	Formability		o	o	□	o	o	o	o		
	General evaluation		o	o	o	o	o	o	o		

* 1: first layer; 2: second layer

* Crystallinity of polylactic acid resin contained therein

JDK 3/28

Page 37, Table 4:

			Examples of the invention						
			8	9	10	11	12	13	14
Biodegradable laminated sheet	Entire sheet	Sheet thickness (μm)	400	300					
		Layer structure	Three layers			Two layers	Three layers		
		Layer arrangement *1)	1/2/1			1/2	2/1/2	1/2/1	
		Ratio of thickness	1/1/1	1/5/1		2/5	3/1/3	1/5/1	
		Db-Da (mass %)	10.8	7	5.9	10.8			
	First	Da (mass %)	1.2	5	1.2				
		Thickness (Total) (μm)	267	86			43	86	

Second layers	Crystallinity*2) (%)		42	30	43	46	42	42	43
	Polyester resin	Type	PBS						
		Content (mass %)	75	50					60
	Db %		12		7.1	12			
	Thickness (Total) (μm)		~~34~~134	214			257	214	
	Crystallinity*2) (%)		1.8	2.4	9.2	1.1	3.4	1	1.1
	Polyester resin	Type	PBS						
		Content (mass %)	75	50					60
Evaluation	Heat resistance 1 (%)		0.7	1	0.9	1.2	1.4	0.9	0.8
	Heat resistance 2		o	o	o	o	o	o	o
	Impact resistance 1 (Kgf·mm)		398	270	198	203	222	220	302
	Impact resistance 2		o	o	o	o	o	o	o
	Formability		o	o	o	o	o	o	o
	General evaluation		o	o	o	o	o	o	o

* 1: first layer; 2: second layer

* Crystallinity of polylactic acid resin contained therein

JDK 3/28

Pagd ~~40~~ 38, Table 5:

			Comparative Examples					
			1	2	3	4	5	6
Biodegradable laminated sheet	Entire sheet	Sheet thickness (μm)	300					
		Layer structure	Single layer			Three layers	Single layer	Three layers
		Layer arrangement*1)	1			1/2/1	1	1/2/1
		Ratio of thickness	–			1/2/1	–	1/5/1
		Db-Da (mass %)	–			10.8	–	4.8